

## ALUJET Dampfbremsbahn 400 mµ

```
Product
discription
```

The ALUJET vapour barrier film in a thickness of 400 m $\mu$  is used as an air barrier and vapour barrier on pitched and flat roofs. The parameters prescribed by DIN 4108 are achieved thanks to the classification in fire rating E according to DIN EN 13501-1 and an sd value of >200 m.



# **Product** High material flexibility; inexpensive; high tear strength; extremely high tensile strengths benefits

### Area of application

Roll content:

Vapour barrier/vapour check for internal use on pitched roofs and for use on the top chords of flat roofs. The requirements of DIN 18234 are NOT met.

Technichal 🕨	Test	Standard	Unit	Value
data				
	Reaction to fire	EN 13501-1 / EN 11925-2		E
	Density		g / cm³	0,94
	water vapor permeability		g / m²d	< 0,21
	Sd-Value	EN 12572 / EN 1931	m	> 200
	Tensile elongation longitudinal	EN12311-1 / EN 13859-1	N / 50 mm	≥ 300
	Tensile elongation transversal	EN12311-1 / EN 13859-1	N / 50 mm	≥ 259
	Elongation longitudinal	EN12311-1 / EN 13859-1	%	≥ 400
	Elongation transversal	EN12311-1 / EN 13859-1	%	≥ 500
	Tear resistance longitudinal	EN 12310-1	Ν	≥ <b>224</b>
	Tear resistance tranversal	EN 12310-1	Ν	≥ <b>216</b>
	Dart Drop		g/mµ	≥ 2,0

#### System components Pitched roof: ALUJET Difutape; ALUJET Alusan; ALUJET Alucral; ALUJET Dichtjet; ALUJET Allfixx. Flat roof: ALUJET Super PE; ALUJET Super PE Plus.

100 m<sup>2</sup>



#### Verarbeitung

<u>Pitched roof:</u>

The ALUJET vapour barrier film is laid parallel to the rafters, starting at adjacent components (gable end).

It must be ensured that the vapour barrier film overhangs by about 20-30 cm in the area of adjacent components (gable end, knee wall, ridge purlin). Fastening of the vapour barrier film begins with the closest rafter to the gable end and is carried out by stapling at intervals of approx. 15 cm. This fastening is continued at each rafter.

It must be ensured that the ALUJET vapour barrier film is installed without resulting in any tension. The overlaps at the end and beginning of the film should be positioned so that they are located directly on the rafters with an overhang of 10 cm. The ALUJET vapour barrier film is not stabilised against UV rays.

When using mat and panel type insulation materials, tensile stresses on the adhesive tape joints are to be expected (e.g. due to the weight of the insulation material). Therefore, additional supporting battens may be necessary on the overlap bond.

Flat roof:

The ALUJET vapour barrier film is laid parallel to the crowns of the profiled sheet. Side laps and end laps are arranged with an overlap of at least 8 cm. It is possible to fix the membrane to the substrate with the double-sided adhesive tape ALUJET Super PE or ALUJET Super PE Plus.

The overlaps are bonded on the crown by applying the ALUJET Super PE or ALUJET Super PE Plus tape between the overlapping membranes using rollers or through compression.

To prevent faulty bonds, the ALUJET vapour barrier film is applied without tensile and shearing forces.

Lagerung Without exposure to UV radiation. This could permanently reduce the properties of the material..

Hinweise	CE	
	05 EN 13984	

Our instructions for use, guidelines for use, product and service information and other technical specifications only serve as a guide, they only describe the properties of our products (value specifications/determinations at time of production) and services and do not constitute guaranteed characteristics. Owing to the wide-ranging areas of application of the individual products and the particular conditions (e.g. usage parameters, material properties etc.), it is incumbent on the user to test our products. Our applications engineering consulting - whether verbal, in writing or by way of tests is offered free of charge and is not legally binding.